



**MAYREX® MW11120GF**

**Acrylonitrile-Butadiene-Styrene 20% Glass Reinforced ( ABS 20% GF )**

Physical Properties	Method	Testing Condition	Unit	Typical Value
---------------------	--------	-------------------	------	---------------

Specific Gravity	ASTM D-792	-	g/cm <sup>3</sup>	1.20
Water Absorption	ASTM D-570	23 °C	%	0.35

**Mechanical Properties**

Tensile Strength	ASTM D 638	-	kg/cm <sup>2</sup>	1000
Tensile Elongation	ASTM D 638	-	%	3
Flexural Modulus	ASTM D 790	-	kg/cm <sup>2</sup>	59000
Flexural Strength	ASTM D 790	-	kg/cm <sup>2</sup>	1400
Izod Impact	ASTM D 256	V-notched, 1/8"	kg.cm/cm	5

**Thermal Properties**

Melt Flow Index	ASTM D 1238	-	g/10min	5
Heat Distortion Temperature	ASTM D-648	18.6kg/cm <sup>2</sup>	°C	105
Flammability	UL-94	-	-	HB

**Processing Properties**

Drying Hour	-	-	Hr	3-4
Drying Temperature	-	-	°C	85
Melt Temperature	-	-	°C	200-240

All information is furnished in good faith, without warranty, representation, inducement or a license of any kind. No guarantee is given that Metro Wealth Polymer products will be suitable in purchasers' formulations or processes for any particular end use.